



2035 W. McDowell Rd. | Phoenix, AZ 85009

Full Color Chip Flooring System

PRODUCT NAME: POLYASPARTIC

DESCRIPTION: Mixing ratio is 1 part A to 1 part B. Kits come in 6 gallons, 3 gallons part A and 3 gallons part B. You will likely mix in smaller amounts, especially for cut-in, just keep the ratios in proportion.

The mixing ratios are as follows:

Mixing- Prime Coat

1. 64 ounces of part A
 2. 4 ounces of Pigment
 3. Mix together
 4. 64 ounces of part B
 5. 10 ounces of Acetone (recommended, not required)
 6. **Mix all together with stir stick back and forth for 2 minutes. Remember to scrape the sides and the bottom of the mixing bucket.**
- You should see coverage rates of around 250 sq. ft / gallon

Mixing- Chip Coat

1. 64 ounces of part A
 2. 4 ounces of Pigment
 3. Mix together
 4. 64 ounces of part B
 7. 4 ounces of Acetone (recommended, not required)
 5. **Mix all together with stir stick back and forth for 2 minutes. Remember to scrape the sides and the bottom of the mixing bucket.**
- You should see coverage rates of around 330-350 sq. ft / gallon

Mixing- Top Coat

1. 64 ounces of part B
 2. 64 ounces of part A
 8. 3 ounces of Acetone (recommended, not required)
 3. **Mix all together with stir stick back and forth for 2 minutes. Remember to scrape the sides and the bottom of the mixing bucket.**
- You you should see coverage rates of around 250 sq. ft / gallon.

If you do a 2nd top coat, do a thin coat, keep the coverage rate to around 350-400 sq. ft / gallon.

Floor chips – full chip floor. Throw approx. 1 lb per 6-7 sq. ft. You should recover 35% - 50% of what you throw.